

Poly floor hard

Monolithic, Non-metallic, Dry Shake

DESCRIPTION

POLY FLOOR HARD is a premixed surface hardener which contains hydraulic binders and synthetic mineral aggregates. It is applied on to fresh concrete to obtain an abrasion and chemicals-resistant floor finish.

COMPOSITION

POLY FLOOR HARD is a blend of graded synthetic mineral aggregates, cement, plasticizers and special additives to provide a material which is easy to trowel to achieve a non porous, hard wearing abrasion and chemicals-resistant floor finish.

USES

- Workshops, garages, chemical factories, warehouses, shipyards, docks
- Power stations, car wash areas and aircraft hangers
- Food processing units, detergent and household manufacturing units, ...etc

FEATURES

- Economical, easy to use and premixed
- Resistant to industrial chemicals, oils, grease
- Wear and tear, abrasion and impact resistant
- Ideal for interior and exterior locations
- Available in various colors
- Forms a monolithic bond with fresh concrete

SPECIFICATIONS

- Color: Grey
(Other colors available upon request)
- Specific Gravity: 1.71
- Compressive strength: 80 N/ mm²
- Abrasion resistance: 300%
Of untreated concrete
- Standards: 85 - 1881 part 116
- ASTM C 779 - 89

APPLICATION

- Base Concrete pre-requisites

The base concrete should have a minimum slump of 75 - 100 mm . The concrete mix

Should be laid and compacted in accordance with good concrete practice and care for the edges and corners. The concrete mix should be designed to minimize segregation and bleeding.

POLY FLOOR HARD APPLICATION

POLY FLOOR HARD should be applied as it to fresh concrete by dry shake method. It should be applied when a light foot traffic leaves an imprint of 3 - 6 mm on the concrete surface.

The application is carried out as follows:

1- Carry out the first broadcast amounting to 2/3 of the specified quantity on the concrete surface. When the broadcast material absorbs moisture from the base concrete, it becomes dark in color. It is then surface treated with the wooden or power float machine.

2- Immediately apply the second cast evenly on the surface by spraying it in a directions perpendicular to the first application. When the surface absorbs moisture it should be floated thoroughly.

3- The final finishing can be carried out with a power float when the floor has stiffened sufficiently to withstand the mechanical weight.

BAY EDGES

Extreme care and attention should be given to bay edges and corners as they endure heavy wear and impact.

- Immediately after leveling the fresh concrete, sprinkle **POLY FLOOR HARD** by hand at a rate of 7 kg/m² in strips of 10cm width alongside the bay edges (i.e. 0.5 kg/running meter).

- Immediately after leveling the fresh concrete, remove a wedge of concrete 10 mm deep at the edges, then apply a stiff mass of **POLY FLOOR HARD** mixed with clean water. This must be fully compacted to the base concrete. The reinforced areas will be further strengthened when subsequent full application is completed.

COVERAGE

3 Kg/m² for light traffic.
5 Kg/m² for medium traffic.
7 Kg/m² for heavy traffic.

PACKAGING

POLY FLOOR HARD is supplied in 25 kg double-layered bags.

STORAGE

Store under cover away from direct sunlight and protect from extreme temperatures.

SHELF LIFE

Up to 12 months if stored properly per recommendations above.

CURING

POLY CURE RB is recommending for use for all types of concrete floor curing.

CLEANING

Any remains or spillage can be removed with water.

HEALTH & SAFETY

As with all construction chemical products, caution should always be exercised. Always use protective clothing such as gloves and goggles, and treat any splashes to the skin or eyes with fresh running water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.



Under technical collaboration with
Polycoo Industries Ltd.

Sole distributor in Egypt: Polycoo Company

www.polycoo.com

5 Kamel Sedki Street, Ramsis Square, Cairo, Egypt

Sales Tel.: ++202-5918653/++2025918053/++20-122-3102700 Fax: ++202-5918053